

Physical Properties	Test Method	Unit	Value
Nominal Density	ASTM D3575-08 Suffix W ISO 845:2006	Kg/m ³	37
Compressive Strength Vertical @ 10% Vertical @ 25% Vertical @ 50% (100 m/min compression speed)	ASTM D3575-08 Suffix D ISO 7214:2007	KPa	50 65 125
Compressive Strength Vertical @ 25% (4th compression) Vertical @ 50% (4th compression) Vertical @ 70% (4th compression)	ISO 3386 1986 part 1 DIN 53577	KPa	30 90 220
Compression Set	ASTM D3575-08 Suffix B (50% compression) ISO 1856:2000 (25% compression)	%	< 20 < 10
Compressive Creep	ASTM D3575-08 Suffix BB 168 hrs	%	< 5 (2 psi / 14 kg/dm ²)
Compressive Creep	ASTM D3575-08 Suffix BB 1000 hrs	%	< 10 (2,5 psi / 17,5 kg/dm ²)
Thermal Stability	ASTM D3575-08 Suffix S ISO2796	%	< 2
Tensile Strength @ peak (MD/CD)	ASTM D3575-08 Suffix T ISO 1798: 2008	KPa	213 165
Tensile Elongation (MD/CD)	ASTM D3575-08 Suffix T ISO 1798: 2008	%	32 33
Tear Strength (MD/CD)	ASTM D3575-08 Suffix G	N/cm	17 14
Water Absorption	ASTM D3575-08 Suffix L ISO 2896: 1986	Volume %	< 3
Fire-test response Characteristics (1) Transportation Automotive	FMVSS 302	-	Pass
Working temperature	-	°C	- 60 + 80

(1) These numerical laboratory fire-test-response characteristics are not intended to reflect hazards presented by this material under actual fire conditions

NOTICE: The data presented for this product is for unfabricated polyethylene foam product. While values shown are typical of this product, they should not be construed as specification limits. Sealed Air makes no warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, with respect to any product, information or recommendations referred to herein, and shall not be liable for any loss or damage, directly or indirectly, related to such product, information or recommendations or for consequential or incidental damages. User should test each application to determine suitability of the product for the intended use.

Sealed Air
Telford Way
Kettering NN16 8UN
United Kingdom

T: +44 1536 315700
E: info-pack@sealedair.com
www.sealedair.com/product-care

E220-EN 05/20

© Sealed Air Corporation 2019. All rights reserved.

